

UNIVERSITÀ DELLA CALABRIA



XXV Congresso Nazionale della Società Chimica Italiana

Arcavacata di Rende
07-12 Settembre 2014

ATTI DEL CONGRESSO

XXV Congresso Nazionale
della Società Chimica Italiana

Università della Calabria
Via Pietro Bucci
87036 Rende (CS), Italy

Arcavacata di Rende
07-12 Settembre 2014

Sponsor Istituzionali



UNIVERSITÀ DELLA CALABRIA



UNIVERSITÀ DELLA CALABRIA



Dipartimento di Chimica
e Tecnologie Chimiche




CONSIGLIO NAZIONALE DEI CHIMICI
PRESSO IL MINISTERO DELLA GIUSTIZIA



Main Sponsor



Other Sponsor



SIGMA-ALDRICH®

Solid state NMR characterization of the waterlogged wooden part of Acqualadrone roman rostrum

Stella Bastone^a, Alberto Spinella^b, Delia F. Chillura Martino ^a, Eugenio Caponetti^{a,b}

a Dipartimento Scienze e Tecnologie Biologiche, Chimiche e Farmaceutiche - STEBICEF, Università degli Studi di Palermo, Parco d'Orleans II, Viale delle Scienze pad. 17, I-90128, Palermo, Italy

b Centro Grandi Apparecchiature-UniNetLab, Università degli Studi di Palermo, Via F. 14, I-90128, Palermo, Italy

stella.bastone@unipa.it

The roman rostrum found in the sea of Acqualadrone (ME) was characterized in our previous papers ^{1,2}. In the present work solid state NMR spectroscopy was applied on a wooden sample of the same artefact collected by coring and divided in four parts in order to correlate the conservation state to the depth. Results were compared with those obtained for a modern wood of the same species.

A structural study was performed by the acquisition of ¹³C Cross Polarization Magic Angle Spinning (¹³C CP MAS NMR) spectra. These spectra were acquired to assign the chemical shifts of the species that are present in the wooden matrix. In addition the spectra analysis allowed us to determine the cellulose crystallinity degree and the lignin condensation degree.

The holocellulose-lignin ratio and the cellulose-lignin residual interactions were evaluated through variable contact time (VCT) experiments and through the relaxation times determination respectively. Furthermore these latter experiments allowed us to evaluate the dynamic modifications occurring in the lignin and in the cellulose during the degradation process.

Solid state NMR results showed a decrease of carbohydrates with a complete cleavage of hemicelluloses. The crystallinity degree decreases in depth while the lignin condensation was not modified. Dynamic relaxation times studies demonstrated cellulose and lignin are still interacting to each other in the deepest samples of the wood.

[1] F. Caruso, M.L. Saladino, A. Spinella, C Di Stefano, P. Tisseyre, P., S Tusa, S. And E. Caponetti, *Archaeometry*, 2011, **53**, 547–562.

[2] P. Frank, F. Caruso, and E. Caponetti, E., *Analytical Chemistry*, 2012, **84**, 4419.