



POLITECNICO DI MILANO

Book of Abstracts

Plenary Talks – page 2

Oral Contributions – page 7

Poster Contributions – page 54

List of presenting authors – page 108

<http://superfox.com.polimi.it>

Microwave response of coaxial cavities made of bulk MgB₂

A. Agliolo Gallitto^a, A. Figini Albisetti^b, G. Giunchi^b, M. Li Vigni^a

^a Dipartimento di Fisica, Università di Palermo, Palermo, Italy

^b EDISON SpA R & D, Milano, Italy

We report on the microwave (mw) properties of coaxial cavities built by using bulk MgB₂ superconductor.

The bulk MgB₂ specimens have been produced by Reactive Liquid Mg Infiltration process [1]. Three different coaxial cavities have been prepared by using bulk MgB₂. In particular, two of them are composed by an outer copper cylinder and an inner MgB₂ rod; two inner rods of lengths 45 mm and 94 mm have been used. The third cavity is constituted by the MgB₂ rod of 45 mm and an outer MgB₂ cylinder about 15 mm longer than the inner rod. Figure 1 shows a picture of the outer MgB₂ cylinder.

The resonant cavities have been characterized measuring their frequency response in the range 1 – 13 GHz by an hp-8719D Network Analyzer, in the temperature range 4.2 – 50 K. The cavities built using the 45 mm rod exhibit four resonant modes, in the range 2.5 - 11 GHz; the spectrum of the cavity with the 94 mm MgB₂ rod shows eight resonant modes in the range 1.3 -11 GHz.

Preliminary results have shown that, at T = 4.2 K, the highest unloaded quality factor of the cavity entirely made of MgB₂ is $Q \approx 80000$ at the resonant frequency $f = 2.55$ GHz. It remains of the order of 10^4 up to about 30 K and reduces by a factor of 60 when the superconductor goes into the normal state.

The results obtained in the coaxial cavity entirely made of MgB₂ will be compared with those already obtained in a MgB₂ cylindrical cavity [2] and discussed with the aim to exploit the material in mw applications.

Recently, we have built a tunable coaxial cavity using a rod of BSCCO and have shown that it can be conveniently used to investigate the mw response of the inner superconducting rod, in both linear and nonlinear regimes [3]. We will use the longer cavity with this aim. In particular, it will be possible to determine the frequency dependence of the mw surface resistance of the MgB₂ in the frequency range 1 - 11 GHz; to our knowledge, this issue is not widely discussed in the literature.



Figure 1: Bulk MgB₂ cylinder used for assembling the coaxial cavity

-
- [1] G. Giunchi, G. Ripamonti, T. Cavallin, E. Bassani, *Cryogenics* **46** (2006) 237.
 - [2] G. Giunchi, A. Agliolo Gallitto, G. Bonsignore, M. Bonura, M. Li Vigni, *Supercond. Sci. Technol.* **20** (2007) L16.
 - [3] A. Agliolo Gallitto, G. Bonsignore, M. Li Vigni, A. Maccarone, , *Supercond. Sci. Technol.* **24** (2011) 095008 (8pp).